

1. PRODUCT NAME

SealMaster Fast-Dry Traffic Paint

2. MANUFACTURER

SealMaster
2520 S. Campbell St.
Sandusky, OH 44870
Phone: 800-395-7325
Fax: 419-626-5477
www.sealmaster.net

Additional Plant Locations: SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone us at 1-800-395-7325 or visit our website at www.sealmaster.net to find the location near you.

3. PRODUCT DESCRIPTION & BENEFITS

SealMaster Fast-Dry Traffic Paint is a premium quality, lead-free, 100% acrylic emulsion designed for striping asphalt and concrete pavement surfaces. Features and benefits include:

- Excellent Durability - Superior wear properties over asphalt and concrete surfaces.
- Fast Dry - Fast dry-to-no-pickup time.
- Enhanced Retention of Glass Beads - Excellent long-term night visibility.
- Environmentally Friendly - Low VOC (less than 100 grams per liter volatile organic content).
- User Friendly - Non-flammable, water clean-up, reduced disposal costs, increased worker safety.
- Meet and exceeds TT-P-1952 D

Basic Uses: Asphalt or concrete highways, roads, streets, parking lots, and more.

Composition: SealMaster Traffic Paint is a water based material comprised of 100% acrylic emulsion resins, specialty pigments, additives, surfactants, mineral fillers, and water.

Sizes: 55-gallon drums, and 5-gallon pails.

Color: White, Yellow.

Limitations: SealMaster Fast-Dry Traffic Paint shall not be applied when temperature is expected to drop below 50°F at any time within a 24 hour period after application.

4. TECHNICAL DATA

SealMaster Fast-Dry Traffic Paint meets and exceeds the chemical composition and performance requirements of Federal Specification TT-P-1952 D.

Environmental Considerations: SealMaster Fast-Dry Traffic Paint is an environmentally friendly 100% acrylic waterborne traffic paint containing less than 100 grams per liter volatile organic content (VOC).

Physical/Chemical Properties: SealMaster Fast-Dry Traffic Paint meets or exceeds the following specifications when tested in accordance with ASTM D562, ASTM D711, ASTM D713, ASTM D969, ASTM D1210, ASTM D1475, ASTM D1640, ASTM D2243, ASTM D3960, ASTM D2486, ASTM D2805, ASTM E70, and ASTM E1347. (see chart below)

5. INSTALLATION

Asphalt and concrete pavement surfaces shall be clean and free

from all loose materials and dirt. New asphalt surfaces should cure sufficiently to be free of light oils on the surface (4 weeks). Allow freshly applied pavement sealer to cure for at least 24 hours prior to applying traffic paint.

Methods: Apply SealMaster Fast-Dry Traffic Paint with spray equipment (with stainless steel components) roller, or brush.

Mixing Procedures: Stir well before using. Use as is. Do not dilute.

Application: Apply Fast-Dry Traffic Paint at a rate of at least 15 mils wet thickness (325 feet of 4-inch line). Apply to properly cleaned pavement with pressurized spray equipment, brush, or roller.

Estimating Material Requirements: One gallon of SealMaster Fast-Dry Traffic Paint will provide 325 feet of 4-inch line at 15 mils wet thickness. *NOTE* - Coverage rates will vary due to pavement porosity and application thickness.

Precautions: Both surface and ambient temperature shall be a minimum of 50°F. Temperature shall

Chemical & Physical Analysis

	White	Yellow
Weight Per Gallon.....	14.1 lbs./gal.	13.5 lbs./gal.
Volatile Organic Content (VOC)	<100 g/l	<100 g/l
Viscosity (KU)	80 - 90	80 - 90
Dry To No Pick-Up Time.....	<6 min.	<6 min.
Scrub Resistance.....	1,000 cycles min.	1,000 cycles min.
Water Resistance, cycles	8 min.	8 min.
Freeze Thaw Cycles.....	5 cycles min.	5 cycles min.
Degree of Bleeding98 min.	.98 min.
Fineness of Dispersion (Hegman)	3 - 4	3 - 4
Contrast Ratio @ 5 mils wet	0.92 min.	0.89 min.
Directional Reflectance.....	.86%	50%
Dry Opacity ..	.0.965 min.	0.965 min.
Total Solids By Weight %.....	77.5	76.5
Total Solids By Volume %.....	61.0	60.9
Pigment Volume Content %	60.0	60.0
Pigment Solids % (by weight).....	61.10	59.4
Non Volatile Vehicle % (by weight).....	42.0	42.0
PH of Paint	9.8 min	9.8 min

SealMaster Fast-Dry Traffic Paint

not drop below 50°F within a 24 hour period following application. Keep Out Of Reach Of Children. Do not store unopened containers in freezing temperatures.

6. AVAILABILITY & COST

Availability: SealMaster Fast-Dry Traffic Paints are supported by a nationwide network of SealMaster manufacturing facilities along with a national network of professional applicators.

Cost: Cost information can be obtained from a local applicator. Contact SealMaster for the representative in your area.

7. WARRANTY

SealMaster Industries warrants that SealMaster Fast-Dry Traffic Paint meets the chemical composition and performance requirements set forth in section 4. Liability to the buyer or user of this product is limited to the replacement value of the product only.

8. TECHNICAL SERVICES

Manufacturer: Complete product specifications, material safety data sheets, and technical assistance is available from SealMaster.

Professional Applicators: Your local applicator is available to provide on-site inspections and recommendations to meet your specific needs.

9. FILING SYSTEMS

- SealMaster Online Specifications at www.sealmaster.net
- Complete SealMaster Product and Equipment Catalog Available
- Sweet's Catalog
- Sweet's CD
- Sweet's Online
- Sweet's Directory

The statements made on this specification sheet are believed to be true and accurate and are intended to provide a guide for approved application practices. As workmanship, weather, construction, condition of pavement, tools utilized, and other variables affecting results are all beyond our control, the manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. The manufacturer expressly disclaims any implied warranties of merchantability or fitness for a particular purpose. Warranty is void on multi-coat applications if material made by other manufacturers is used with this product.

Form No.: SMT-244

Revised: 1/02

Supersedes: SMT-27 (4/99), and SMT-244 (10/01)

Copyright © 2001, SealMaster Industries, Inc. All rights reserved.

SealMaster Industries, Inc.
2520 South Campbell ST.
Sandusky, OH 44870

Phone: 1-800-395-7325

FAX: 1-419-626-5477

www.sealmaster.net

SealMaster[®]

Pavement Products & Equipment