

1. PRODUCT NAME
Line Block-Out Paint

2. MANUFACTURER
SealMaster
2520 S. Campbell St.
Sandusky, OH 44870
Phone: 800-395-7325
Fax: 419-626-5477
www.sealmaster.net

Additional Plant Locations:
SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone us at 1-800-395-7325
or visit our website at
www.sealmaster.net to find the
location near you.

3. PRODUCT DESCRIPTION &
BENEFITS
Line Block-Out Paint is a 100% acrylic black paint designed to black-out unwanted traffic lines and markings.

Basic Uses: For blacking out unwanted lines on highways, roads, and parking lots.

Composition: Line Block-Out Paint is comprised of 100% acrylic emulsion resins, specialty pigments, surfactants, and fillers.

Sizes: Available in 55-gallon drums, and 5-gallon pails.

Color: Black.

Limitations: Line Block-Out Paint shall not be applied when temperature is expected to drop below 50°F at any time within a 24 hour period after application.

4. TECHNICAL DATA
Environmental Considerations: Line Block-Out Paint is an environmentally friendly 100% acrylic emulsion traffic paint containing less than 150 grams per liter volatile organic content (VOC).

Physical/Chemical Properties: Line Block-Out Paint meets or exceeds the following specifications when tested in accordance with ASTM D562, ASTM

D711, ASTM D969, ASTM D1475, ASTM D3960, ASTM D2486, and ASTM E70. (see chart below)

5. INSTALLATION
Asphalt and concrete pavement surfaces shall be clean and free from all loose materials and dirt. New asphalt surfaces should cure sufficiently to be free of light oils on the surface (4 weeks). Allow freshly applied pavement sealer to cure for at least 24 hours prior to applying traffic paint.

Methods: Apply Line Block-Out Paint with pressurized spray equipment, brush, or roller.

Mixing Procedures: Stir well before using. Use as is. Do not dilute.

Application: Apply to properly cleaned pavement with pressurized spray equipment, brush, or roller.

Estimating Material Requirements: One gallon of SealMaster Traffic Paint will provide 325 feet of 4-inch line at 15 mils wet thickness.
NOTE - Coverage rates will vary due to pavement porosity and application thickness.

Precautions: Both surface and ambient temperature shall be a minimum of 50°F. Temperature shall not drop below 50°F within a 24 hour period following application. Keep Out Of Reach Of Children. Do not store unopened containers in freezing temperatures.

6. AVAILABILITY & COST

Availability: Line Block-Out Paint is supported by a nationwide network of SealMaster manufacturing facilities along with a national network of professional applicators.

Cost: Cost information can be obtained from a local applicator. Contact SealMaster for the representative in your area.

7. WARRANTY
SealMaster Industries warrants that Line Block-Out Paint meets the chemical composition and performance requirements set forth in section 4. Liability to the buyer or user of this product is limited to the replacement value of the product only.

Chemical & Physical Analysis

Weight Per Gallon.....	11.90 lbs/gal.
Volatile Organic Content (VOC).....	<150 g/l
Viscosity (KU)	70 - 90 KU
Dry To No Pick-Up Time.....	<30 min.
Scrub Resistance.....	1,000 cycles min.
Degree of Bleeding98 min.
Water Resistance, cycles	8 min.
PH of Paint	9.6 min.
Solids (by weight) %	57 - 59

Line Block-Out Paint

8. TECHNICAL SERVICES

Manufacturer: Complete product specifications, material safety data sheets, and technical assistance is available from SealMaster.

Professional Applicators: Your local applicator is available to provide on-site inspections and recommendations to meet your specific needs.

9. FILING SYSTEMS

- SealMaster Online Specifications at www.sealmaster.net
- Complete SealMaster Product and Equipment Catalog Available
- Sweet's Catalog
- Sweet's CD
- Sweet's Online
- Sweet's Directory

The statements made on this specification sheet are believed to be true and accurate and are intended to provide a guide for approved application practices. As workmanship, weather, construction, condition of pavement, tools utilized, and other variables affecting results are all beyond our control, the manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. The manufacturer expressly disclaims any implied warranties of merchantability or fitness for a particular purpose. Warranty is void on multi-coat applications if material made by other manufacturers is used with this product.

Form No.: SMT-245
Revised: 10/01

Copyright © 2001, SealMaster Industries, Inc. All rights reserved.

SealMaster Industries, Inc.
2520 South Campbell ST.
Sandusky, OH 44870

Phone: 1-800-395-7325
FAX: 1-419-626-5477

www.sealmaster.net