

1. PRODUCT NAME

SealMaster IV Concentrate
Pavement Sealer

2. MANUFACTURER

SealMaster
2520 S. Campbell St.
Sandusky, OH 44870
Phone: 800-395-7325
Fax: 419-626-5477
www.sealmaster.net

Additional Plant Locations:
SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone us at 1-800-395-7325
or visit our website at
www.sealmaster.net to find the
location near you.

3. PRODUCT DESCRIPTION & BENEFITS

SealMaster IV Concentrate pavement sealer is a clay-stabilized asphalt based emulsion fortified with coal tar for added fuel resistance and durability. IV Concentrate is formulated to be job-mixed with water and aggregate.

Basic Uses: SealMaster IV Concentrate is designed to beautify and protect asphalt pavement surfaces including parking lots, airports, driveways, shopping malls, roadways, and more.

Composition: SealMaster IV Concentrate is a clay-stabilized asphalt and coal tar emulsion blend pavement sealer fortified with special surfactants to promote superior adhesion and durability. Select aggregate is job-mixed to produce a slip-resistant coating.

Sizes: SealMaster IV Concentrate is available in 4,000 gallon bulk tankers, 55-gallon drums, and 5-gallon pails.

Color: SealMaster IV Concentrate dries to a deep, rich black color.

Limitations: SealMaster IV Concentrate shall not be applied when temperature is expected to

drop below 50°F at any time within a 24 hour period after application.

4. TECHNICAL DATA

SealMaster IV Concentrate meets the performance standards of ASTM D-2939.

Environmental Considerations:
SealMaster IV Concentrate does not contain asbestos. SealMaster IV Concentrate is an environmentally friendly water based pavement sealer containing less than 150 grams per liter volatile organic content (VOC).

Physical/Chemical Properties:
SealMaster IV Concentrate is a premium quality pavement sealer that meets the following material requirements when tested in accordance with ASTM D 140, ASTM D 466, ASTM B117, ASTM D 529, ASTM D 2939, and ASTM D244 procedures. (see chart below)

5. INSTALLATION

Surface must be clean and free from all loose material and dirt. Pavement surface repairs should be made with a suitable hot or cold

asphalt mix. Cracks should be filled with SealMaster hot pour or cold applied crack fillers. Treat all grease, oil, and gasoline spots or stains with SealMaster Petro Seal™ or Prep Seal™.

Methods: SealMaster IV Concentrate shall be applied by either pressurized spray application equipment or self-propelled squeegee equipment. Pressurized spray equipment shall be capable of spraying pavement sealer with sand added. Equipment shall have continuous agitation or mixing capabilities to maintain homogeneous consistency of pavement sealer mixture throughout the application process. Self-propelled squeegee equipment shall have at least 2 squeegee or brush devices (one behind the other) to assure adequate distribution and penetration of sealer into bituminous pavement. Hand squeegees and brushes shall be acceptable in areas where practicality prohibits the use of mechanized equipment.

TEST	SPECIFICATIONS	RESULT
Material	Material shall be homogenous and show no separation or coagulation that cannot be overcome by moderate stirring.	PASSES
Chem. & Physical Analysis		
- Non Volatiles %	47-53%	PASSES
- Ash Non Volatiles %	30 - 60	PASSES
- Specific Gravity 25°C	1.18 Minimum	PASSES
Drying Time	8 Hr. Max.	PASSES
Adhesion & Resistance to Water	No Penetration or Loss of Adhesion	PASSES
Resistance to Heat	No Blistering or Sagging	PASSES
Flexibility	No Cracking or Flaking	PASSES
Resistance to Impact	No Chipping, Flaking or Cracking	PASSES

SealMaster IV™ Concentrate Pavement Sealer

Mixing Procedures:

- For optimum results, SealMaster IV Concentrate Pavement Sealer shall be mixed in accordance with the following mix design (based on 100 gallons for ease of calculation):

SealMaster IV Concentrate.....100 gals.
Water.....20-25 gals.
Top Tuff Polymer Additive.....2 gals.
Sand*.....300-500 lbs.
*(40-70 mesh AFS rating)

IMPORTANT: The above mix design is a typical recommendation. Alternative mix designs may be substituted to account for local pavement conditions and use of other pavement sealer additives. However, in all cases sand shall be used in the mix design.

NOTE: Top Tuff is manufactured by SealMaster Industries, Inc. and is available from your regional SealMaster location.

Application: For optimum performance and durability apply two coats of properly mixed SealMaster IV. A third coat of mixed SealMaster IV may be applied to high traffic areas such as entrances, exits, and drive lanes.

Application Rate of Mixed SealMaster IV: Apply properly mixed SealMaster IV (LV Concentrate, Water, Sand, Additive) at a rate of .11 to .13 gallon per square yard (70-82 square feet per gallon) per coat.

Estimating Material Requirements: To estimate gallons of SealMaster IV Concentrate required to cover a specific area use the following coverage rate:

- One gallon of SealMaster IV will cover approximately 100-120 square feet (11.1 to 13.3 square yards) per coat when properly mixed and applied.

Note: Coverage rates may vary due to pavement age and porosity.

Precautions: Both surface and ambient temperature shall be a

minimum of 50°F. Temperature shall not drop below 50°F in a 24 hour period following application. New asphalt surfaces should be allowed to cure a minimum of four weeks under ideal weather conditions (70°F) before applying MasterSeal Concentrate. Keep Out Of Reach Of Children. Do not store unopened drums or pails in freezing temperatures.

6. AVAILABILITY & COST

Availability: SealMaster IV Concentrate is supported by a nationwide network of SealMaster manufacturing facilities along with a national network of professional applicators.

Cost: Cost information can be obtained from a local SealMaster IV Concentrate applicator. Contact SealMaster for the SealMaster IV Concentrate representative in your area.

7. WARRANTY

SealMaster Industries warrants that SealMaster IV Concentrate meets the chemical composition and performance requirements set forth in section 4. Liability to the buyer or user of this product is limited to the replacement value of the product only.

8. MAINTENANCE

Periodic cleaning of parking lot surface will ensure optimum product service life.

9. TECHNICAL SERVICES

Manufacturer: Complete product specifications, material safety data sheets, and technical assistance is available from SealMaster.

Professional Applicators: Your local SealMaster IV Concentrate applicator is available to provide on-site inspections and recommendations to meet your specific needs.

10. FILING SYSTEMS

- Sweet's Catalog
- Sweet's CD
- Sweet's Online
- Sweet's Directory
- SealMaster Online Specification at www.sealmaster.net
- Complete SealMaster Product and Equipment Catalog Available

The statements made on this specification sheet are believed to be true and accurate and are intended to provide a guide for approved application practices. As workmanship, weather, construction, condition of pavement, tools utilized, and other variables affecting results are all beyond our control, the manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. The manufacturer expressly disclaims any implied warranties of merchantability or fitness for a particular purpose. Warranty is void on multi-coat applications if material made by other manufacturers is used with this product.

Form No.: SMT-120

Revised: 10/01

Supersedes: SMT-53(6/99), SMT-63(9/00), SMT-120 (7/01)

Copyright © 2001, SealMaster Industries, Inc. All Rights Reserved.

SealMaster Industries, Inc.
2520 South Campbell ST.
Sandusky, OH 44870

Phone: 1-800-395-7325

FAX: 1-419-626-5477

www.sealmaster.net

SealMaster®

Pavement Products & Equipment