



1. PRODUCT NAME:  
TrackMaster

2. MANUFACTURER:  
SealMaster  
2520 S. Campbell St.  
Sandusky, OH 44870  
Phone: 800-395-7325  
Fax: 419-626-5477  
www.sealmaster.net

*Additional Plant Locations:*  
SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone us at 1-800-395-7325 or visit our website at www.sealmaster.net to find the location near you.

3. PRODUCT DESCRIPTION & BENEFITS:  
TrackMaster is a fibrated asphalt emulsion manufactured with graded rubber particles, fine silica sand and fillers. Fortified as supplied with acrylic latex, TrackMaster imparts exceptional flexibility and durability to finished surfaces.

*Color:* Black

*Uses:* TrackMaster is designed for protecting and beautifying asphalt bound running tracks and field event surfaces. TrackMaster protects against oxidation and moisture penetration of asphalt surfaces. TrackMaster also reduces maintenance costs and prolongs the life expectancy of line striping.

4. SURFACE PREPARATION:  
Pavement surface must be cleaned entirely of dust, dirt, debris and all loose materials and vegetation. New asphalt must cure 30 days before application. Old, oxidized asphalt surfaces may require a coat of Asphalt Binder (see Technical Bulletin CMT-12). Depressions and shallow, damaged areas in the asphalt surface can be corrected by patching with Lane One (see Technical Bulletin CMT-16).

5. MIXING PROCEDURES:  
Dilute TrackMaster with water using the following ratio: 4 parts TrackMaster to 1 part water.

6. APPLICATION:  
As a coating, TrackMaster is applied using a soft rubber squeegee. Some situations may require a second coat of TrackMaster. A second coat would be applied in the same manner as the first coat only after the first coat had thoroughly dried. It is recommended that the coated surface be allowed to cure for 24 hours before opening up for use.

7. IMPORTANT:  
Stir before using. Temperatures must be above 50°F. both during application and for a period of at least 24 hours after application. Do not apply if rain is imminent or forecast. Keep from freezing. Close container when not in use.

8. DRYING TIME:  
Forty-five to ninety (45 to 90) minutes under optimum conditions.

9. COVERAGE:  
First coat coverage will normally range from 0.15 to 0.25 gallons per square yard depending on the age, roughness, and porosity of the surface. Coverage on successive coats will range from 0.15 to 0.20 gallon per square yard. Yield is based on undiluted TrackMaster

10. CAUTION:  
Do not store in direct sunlight or where temperatures exceed 100°F. Do not apply if rain is imminent or forecast. Keep from freezing. Close container when not in use.

11. WARRANTY:  
The statements made on this technical bulletin are believed to be true and accurate, and are intended to provide a guide for approved construction practices. SealMaster® does not make nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material, as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. SealMaster® warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall SealMaster® be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or equipment furnished or work

### Chemical Characteristics:

	% Weight (Nominal)
Asphalt/Acrylic Emulsion (61.9% Non Volatile) .....	41.86
Emulsifier/Suspension Additive.....	9.99
Organic Filler Material.....	4.99
Mineral Inert Fillers.....	20.00
Miscellaneous Additives.....	0.25
Water.....	22.91

### Product Data:

Type .....	Asphalt/Acrylic Emulsion
Weight per gallon at 77°F.....	10.36 lbs.
% Non Volatile Material .....	61.00
Viscosity at 77°F (Kreb's Units).....	110-120
Odor .....	Asphalt
Flammability .....	Non-Flammable
Flash Point .....	None
Effects of Freezing .....	Damaging
Storage Life .....	One Year
Colors .....	Black

# *TrackMaster*

performed. SealMaster® shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

Copyright© 2003, SealMaster Industries, Inc. All rights reserved.

*SportMaster is a division of:*  
SealMaster Industries, Inc.  
P.O. Box 2277  
Sandusky, OH 44870

Phone: 1-800-395-7325  
FAX: 1-419-626-5477

[www.sportmaster.net](http://www.sportmaster.net)

