



# TrackMaster Plus

CMT - 20

Revised: 6/03

1. PRODUCT NAME:  
TrackMaster Plus

2. MANUFACTURER:  
SealMaster  
2520 S. Campbell St.  
Sandusky, OH 44870  
Phone: 800-395-7325  
Fax: 419-626-5477  
www.sealmaster.net

*Additional Plant Locations:*  
SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone us at 1-800-395-7325 or visit our website at [www.sealmaster.net](http://www.sealmaster.net) to find the location near you.

3. PRODUCT DESCRIPTION & BENEFITS:  
TrackMaster Plus is a colored acrylic emulsion manufactured with graded rubber particles designed to impart exceptional flexibility and durability to asphalt running tracks, and other sport surfaces.

*Color:* Forest Green, Light Green, Red, Beige, Blue, Brown, Maroon, and Gray.

*Uses:* TrackMaster Plus is designed for beautifying and protecting asphalt bound running tracks and field event surfaces. TrackMaster Plus protects against oxidation and moisture penetration of asphalt surfaces. TrackMaster Plus also reduces maintenance costs and prolongs the life expectancy of line striping.

4. SURFACE PREPARATION:  
Pavement surface must be cleaned entirely of dust, dirt, debris and all loose materials and vegetation. New asphalt must cure 30 days before application. Old, oxidized asphalt surfaces may require a coat of Acrylic Adhesion Promotor (see Technical Bulletin CMT-21). Depressions and shallow, damaged areas in the asphalt surface can be corrected by patching with Lane One (see Technical Bulletin CMT-16).

5. MIXING PROCEDURES:

Dilute TrackMaster Plus with water using the following ratio: 4 parts TrackMaster Plus to 1 part water.

6. APPLICATION:  
As a coating, TrackMaster Plus is applied using a soft rubber squeegee. A minimum of two coats are recommended. Allow the coated surface to cure for 24 hours before opening up for use.

7. IMPORTANT:  
Stir before using. Temperatures must be above 50°F. both during application and for a period of at least 24 hours after application. Do not apply if rain is imminent or forecast. Keep from freezing. Close container when not in use.

8. DRYING TIME:  
Forty-five to ninety (45 to 90) minutes under optimum conditions.

9. COVERAGE:  
First coat coverage will normally range from 0.15 to 0.25 gallons per square yard depending on the age, roughness, and porosity of the surface. Coverage on successive coats will range from 0.10 to 0.20 gallon per square yard. Yield is based on undiluted TrackMaster.

10. CAUTION:  
Do not store in direct sunlight or where temperatures exceed 100°F. Do not apply if rain is imminent or forecast. Keep from freezing. Close container when not in use.

11. WARRANTY:  
The statements made on this

technical bulletin are believed to be true and accurate, and are intended to provide a guide for approved construction practices. SealMaster® does not make nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material, as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. SealMaster® warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall SealMaster® be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or equipment furnished or work performed. SealMaster® shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

Copyright© 2003, SealMaster Industries, Inc. All rights reserved.

*SportMaster is a division of:*  
SealMaster Industries, Inc.  
P.O. Box 2277  
Sandusky, OH 44870

Phone: 1-800-395-7325  
FAX: 1-419-626-5477

[www.sportmaster.net](http://www.sportmaster.net)

---

### Product Data:

---

Type .....	Acrylic Emulsion
Weight per gallon at 77°F.....	9.3 lbs.
% Non Volatile Material .....	35
Viscosity at 77°F (Kreb's Units).....	110-120
Flammability .....	Non-Flammable
Flash Point .....	None
Storage Life .....	One Year

---